

Degradation of phosphorus based flame retardant by IR radiation

*Original*

Degradation of phosphorus based flame retardant by IR radiation / Yasin, Sohail; Rovero, Giorgio; Nemeshwaree, Behary; Anne, Perwuelz; Stéphane, Giraud. - (2015). (Intervento presentato al convegno AUTEX World Textile Conference 2015).

*Availability:*

This version is available at: 11583/2670416 since: 2017-05-07T09:16:42Z

*Publisher:*

AUTEX

*Published*

DOI:

*Terms of use:*

openAccess

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

*Publisher copyright*

(Article begins on next page)



# DEGRADATION OF PHOSPHORUS BASED FLAME RETARDANT BY IR RADIATION

Sohail Yasin<sup>1, 2, 3</sup>, Nemeshwaree Behary<sup>1, 2</sup>,  
Stephane Giraud<sup>1, 2</sup>, Anne Perwuelz<sup>1, 2</sup>, Giorgio  
Rovero<sup>3</sup>

<sup>1</sup>ENSAIT-Ecole Nationale Supérieure des Arts et Industries  
Textiles, Roubaix 59100, France.

<sup>2</sup>Université Lille Nord de France, F-59000 Lille, France.

<sup>3</sup>Politecnico di Torino, Corso Giuseppe Pella, 2b - 13900  
Biella, Italy.



# Summary

## Abstract

It is well-known that presence of discarded textile products in municipal landfills pose environmental problems due to leaching of chemical products from the textile to the environmental. Incineration of such textiles is considered to be an efficient way to produce energy and reduce environmental impacts of textile materials at their end-of life stage. However presence of flame retardant products on textiles would decrease the energy yield and emit toxic gases during the incineration stage. Additionally, some non-durable flame retardants can be removed by wet treatments (e.g. washing), these substances pollute water and pose concerns towards the environmental health. Our study shows that infrared radiation can be used efficiently to degrade flame retardant products on the textiles. This method is finalized to minimize the decrease in energy yield during the incineration or gasification processes of flame retardant cotton fabrics.


## Concerns

The consumption of FRs in Europe in 2006 was 465,000 tons, 10% by weightage of which were brominated FRs [1]. FRs have different chemical composition: they contain halogens (bromine and chlorine), phosphorus, nitrogen, aluminum, magnesium, boron, antimony, molybdenum, or recently developed nano-fillers.

Non-durable flame retardant finishes such as ammonium phosphates are mostly used in disposable medical gowns, curtains and carpets, upholstery, bedding and party costumes [2].

The washed off DAP or APP is a serious threat to the water system and soil. If left on the fabric and discarded for disposal (landfill or incineration) will emanate toxic gases increasing the environmental impact.

According to EUROPA & DEFRA [6, 7], a better alternative of disposal is to recycle discarded products rather than producing new ones. When it comes to waste management hierarchy, direct disposals is the least desired option for the waste and discarded products.



Europe's FRs consumption in 2006, 465k tons [1]




Waste management hierarchy [6, 7]

# Introduction

## Sources

In one LCA study, non-durable flame retardants such as ammonium phosphate appeared to have high impact on the environment. The environmental impacts in many categories such as global warming (GWP100), ozone layer depletion (ODP), human toxicity, marine and aquatic ecotoxicity, abiotic depletion and energy use [3, 4]



Overall impact of ammonium phosphate salt FR from cradle-to-gate life cycle assessment [5]

## Objectives

- ❖ The aim of this work was to degrade FR from the textile before it goes through incineration process, so it can be used as fuel alternative.
  - ❖ The proposed pathway of the degradation of FR of the fabric can be a supportive route to decrease environmental impacts as well.
- AS;
- ❖ Incineration of textile products is an efficient way to produce energy using discarded textiles, but incineration of the FR textiles would affect the energy generation and evolves toxic emissions.
  - ❖ Non-durable FRs can be removed by water treatments, but can pollute the water posing concerns towards environmental sustainability. In addition, the toxicity of FRs is yet to be fully investigated.

# Experimental


## Materials & Methods

### Flame retardant and application

The non-durable FR type, ammonium phosphate dibasic (DAP) with CAS. Number 7783-28-0 was provided by Riedel-de Haën, Germany. The cotton sample used was plain woven dyed 110 g/m<sup>2</sup> fabric. The FR treated cotton samples were conditioned in dry atmosphere or at 100 % relative humidity (RH).

### Infrared emitter

Medium wave (50 Hz) infrared heating element was used, each of them having a maximum heating capacity of maximum 1000 W, 230 V. As the IR heating device has three IR emitters, the total capacity was 3 kW. The rectangular geometric assembly of the IR source used was of 533 mm long (a) and 315 mm wide (b).



Schematic illustration of FR degradation with IR radiation

### View Factor

To evaluate the amount of emitted energy, which reaches the product, a geometric relationship can be used. This expression is called view factor and can be calculated from [8];


$$F_{1-2} = \frac{2}{\pi XY} \left\{ \ln \left[ \frac{(1+X^2)(1+Y^2)}{1+X^2+Y^2} \right]^{1/2} + X \sqrt{1+Y^2} \tan^{-1} \frac{X}{\sqrt{1+Y^2}} \right. \\ \left. + Y \sqrt{1+X^2} \tan^{-1} \frac{Y}{\sqrt{1+X^2}} - X \tan^{-1} X - Y \tan^{-1} Y \right\}$$

Where,  $X = a/c$  &  $Y = b/c$

## Results

### View Factor


The FR treated cotton samples (dry or with 100 % RH) were placed at a distance of 300 mm. At this distance, the cotton sample can intercept 28 % of the radiated energy absorbed from the emitting source.



View factors of the IR emitter at different heights

### Flame test

The flame test results of FR treated cotton dry specimen (1D to 5D samples) and with 100 % RH (1M to 5M samples), shows that samples with 100 % RH subjected to 15-20 minutes IR radiation were completely burnt during the flame test.



Degradation of FR with IR radiation with respect to time



# Discussion & Conclusions

## Degradation of FR

Decomposition of ammonium phosphates has been reported at high temperatures, releasing ammonia or phosphoric acid, depending on environment conditions. It is expected that ammonium phosphate dibasic upon reaching certain temperature on cellulosic materials produces cellulose phosphate by phosphorylation [2].

Ammonium phosphate dibasic as FR needs being saturated by moisture to degrade when subjected to IR radiation.

Flame test of flame retarded samples by IR radiation.  
Samples in dry conditions (D) and moist conditions (M)

Samples	Weight (g)	Radiation time (min)	Distance burnt (mm)
1D	7.44	0	50
2D	7.31	5	60
3D	7.01	10	60
4D	7.64	15	70
5D	7.45	20	70
1M	7.12	0	60
2M	7.54	5	70
3M	7.56	10	150
4M	6.95	15	Complete
5M	7.42	20	Complete

## Future perspectives

- ❖ Life Cycle Assessment will be conducted hereafter to check the benefits of the method proposed.
- ❖ A simple method to improve the energetic yield of a flame retardant textile during incineration, the economical aspect of this step which is preliminary to any thermal treatment has still to be investigated.
- ❖ Gasification of discarded textiles is on its way to generate syngas: in this view cotton treated with FR may encounter some difficulty in the process.

## Conclusions

- ❖ Degradation or removal of the FR finish from textiles can be a suitable route to decrease the environmental impact at their end of life.
- ❖ IR radiation can be used to degrade FR ammonium phosphate dibasic from the cotton fabrics. Decreasing the distance between the sample and IR emitter enhances the degradation rate.
- ❖ To maintain the cellulosic nature of cotton unchanged, 15 minute IR radiation time was enough to degrade the FR on the fabric at a certain distance from emitter.

## Acknowledgments

One of the authors (S.Y) acknowledges with his profound gratitude the European Union's program SMDTex under Erasmus Mundus and technician Mr. Christian Catel, who helped in carrying out some tests presented in this work.

## References

1. Van der V. et al., Chemosphere, 2012,88, 1119.
2. Edward D. et al., Flame Retardants in Commercial Use or Development for Textile. 2008 26: 243 Journal of Fire Sciences.
3. Hakan S. et al., Fire safety of upholstered furniture, A Life-Cycle Assessment–Summary Report, IVL.
4. RedFR–Gnosys Summary Work Package D. Life Cycle Assessment RedFR Final Consortium Meeting, 2 February 2011.
5. Gary S. et al., The role of LCA methods in assessing the sustainability of FRs. Materials KTN Meeting on Fire Retardant Materials: Safety vs Sustainability, Bolton, 6 October 2011.
6. EUROPA. Directive 2008/98/EC of the European Parliament and of the Council of 19 November 2008 on waste and repealing certain Directives..
7. DEFRA. Guidance on applying the waste hierarchy, 15 June 2011.
8. Whitaker. S., 1983, Fundamental Principles of Heat Transfer, Krieger Publishing Company, Malabar.